Available online at www.joac.info

ISSN: 2278-1862



Journal of Applicable Chemistry

2018, 7 (2): 397-402 (International Peer Reviewed Journal)



Green Synthesis of Fe₂O₃ Nanoparticles and its Application towards Kinetic Studies on Degradation of Methyl Orange

Yogesh. B. More¹ and Hemant. P. Narkhede^{2*}

 Department of Chemistry, M. J. College, Jalgaon- 425 001 (M. S.), INDIA
 Smt. P. K. Kotecha Mahila Mahavidyalaya, Bhusawal-425201 (M. S.), INDIA Email: narkhede.hemant@rediffmail.com

Accepted on 12th March, 2018

ABSTRACT

Worldwide researchers have been engaged in developing and improving a more efficient method to deal with increasingly rigorous organic dye pollution. In the present work, focus was on benign synthesis of iron oxide (Fe_2O_3) nanoparticles and environmental remediation by degradation of dyes like methyl orange found in waste water of dyes, textile, and pharmaceutical and chemical industries using synthesized iron oxide nanoparticles. These Fe_2O_3 nanoparticles were found to be acts as a prospective catalyst for the degradation of methyl orange in the presence of sodium borohydride. Rate constants for the catalyzed and uncatalyzed reactions were determined. The catalyzed reaction spectrum had shown abrupt fall in absorbance value confirming catalytic effect of Iron oxide nanoparticles. No significant change in the absorbance in case of uncatalyzed reaction was observed, indicating very slow reduction rate of methyl orange.

Graphical abstract



Schematic Representation of Synthesis of Fe₂O₃ Nanoparticles.

Keywords: Methyl orange, Iron nanoparticles, UV-Visible Spectroscopy, Rate Constant.

INTRODUCTION

In latest years, nanoparticles have been the center of attention of researchers in the field as the conversion from microparticles to nanoparticles was seen to lead to massive changes in the physical and chemical properties of a material. Recently, the application of nanomaterials in wastewater treatment has attracted significant attention due to the advantages of large surface areas and more activated functioned sites [1]. Among the different pollutant released to the environment from a variety of industrial applications are dyes which can be considered as dangerous water contaminants. They cause many health disorders such as dysfunction of the kidney, reproductive system, liver, brain, central nervous system even presents at low concentrations [2]. The field of nanoscience has blossomed over the last two decades and the importance of nanotechnology increases in areas such as computing, sensors, biomedical and many other applications. In the past decade, magnetic iron oxide micro and nanoparticles have attracted much consideration because of their distinctive magnetic properties and well-known application in different fields. Magnetic iron oxide nanoparticles are proficient, readily available and have high surface-area resulting in high catalyst loading capacity and excellent stability to heterogeneous supports for catalysts preparation [3]. Accordingly, the application of magnetic nanoparticles catalysis has become an interesting filed of research besides other advantages of nanocatalysts. A series of functionalized Fe₂O₃ nanoparticle have been employed in a range of organic transformations, showing excellent catalytic activities in oxidation [4], dihydroxylation of olefins [5] and amination [6].

Azo dyes are characterized by one or more Azo group (-N=N-) are leading class of colorants used in tattooing, cosmetics, foods and consumer products [7]. Textile industries produce large volume of colored dye effluents, which are toxic and non-biodegradable. These dyes create rigorous environmental pollution problems by releasing toxic and potential carcinogenic substances into aqueous phase [8]. In many applications, once dying is complete a large amount of dye contaminated wastewater must be disposed and because of their high solubility in water, they are transported over long distances when discharged into water. Colored waste water in the ecosystem is a source of artistic pollution, eutrophication and perturbations in aquatic life [9]. Many dyes are cleverly designed to be highly stable towards light, aerobic biodegradation, and common oxidants such as hydrogen peroxide or even hypochlorite, making chemical removal extremely difficult. The traditional physical, chemical and biological methods of waste water treatment have very little degradation effect on this type of pollutants. On the contrary, the technology at nanoscale using spectroscopy techniques, especially UV-visible spectroscopy for degradation study has proved to be effective as compared with any conventional waste water treatment technique [10].



Figure 1: Molecular Structure of Methyl Orange as Azo dye

Methyl orange, being a typical Azo dye for the one Azo bonds (-N=N-) chromophores in its molecular structure is selected as a model dyeing pollutant to evaluate the catalytic activity of the iron nanoparticles. The molecular structure of methyl orange is shown in figure1. It is soluble in water to give intense orange color and used to dye wool, silk etc. and also used as stain as well as an indicator [11]. In present work, we report the degradation of methyl orange by synthesized iron nanoparticles through green approach, with help of UV–Visible spectroscopy. The rate constants for catalyzed and

uncatalyzed reactions have been determined. The high catalytic behavior of iron nanoparticles is also confirmed.

MATERIALS AND METHODS

All chemicals used in the study were reagent grade without further purification. Sodium borohydride (99.99 %), sodium carboxymethyl cellulose (CMC) (MW = 90,000), sodium borohydride (NaBH₄), methyl orange were purchased from Aldrich, USA. All chemicals have high percentage of purity.

Synthesis of Fe₂O₃ Nanoparticles: Iron oxide (Fe₂O₃) nanoparticles were prepared by controlled oxidation of iron nanoparticles in the aqueous phase. Typically, stabilizer 0.5 g of carboxy methyl cellulose was dissolved in 100mL of deionized water followed by addition of FeCl₂ (0.2 M,20 mL) N₂ was purged for 15 min to promote the formation of Fe²⁺ - CMC complex. 50 mL of NaBH₄ (0.2 M) was then added into this precursor solution drop wise (5 mL min⁻¹) and the black iron NPs were formed immediately [12]. After NaBH₄ was consumed, the compressed air was bubbled into the solution at a flow rate of 40 mL min⁻¹. The solution turned brown due to the oxidation. To stop the oxidation, the particles were centrifuged and washed with ethanol twice. After washing, the particles were redistributed in ethanol and dried in the oven at 90⁰C.



Figure 2. Schematic Representation of Synthesis of Fe₂O₃ Nanoparticles.

Degradation of Methyl Orange by Fe₂O₃NPs: A mixture containing 1.5 ml of 1 x 10^{-5} M Methyl Orange Solution and 1 ml of 0.01M sodium borohydride, 2mg of Fe₂O₃ nanoparticles was added in a quartz cuvette. Total volume of the mixture was made up to 3.2 ml by adding the required amount of double distilled water. The reaction was studied in a spectrophotometer cuvette using Shimadzu UV-1800, UV-Visible spectrophotometer at 303K temperature.

RESULTS AND DISCUSSION

FESEM Analysis: The particle size of the Fe_2O_3 particles was in the range of 50-100 nm (Fig.3). The FE-SEM image also reveals that iron nanoparticles tend to from a chainlike aggregate due to the magnetic attractive force between particles. These chain-like Fe_2O_3 Nanoparticles aggregates were also observed by others [13].

Analysis of degradation of methyl orange by sodium borohydride: The reduction of organic dyes by excess of NaBH₄ is widely used for evaluating the catalytic efficiency of metal nanoparticles provided their reduction reaction is thermodynamically favorable but not kinetically and their major spectral bands do not overlap with the SPR band of metal nanoparticles [14]. The aqueous solution of methyl orange shows strong absorptions UV–visible spectrum at 464 nm and 260 nm. The λ max at 464 nm is due to the absorption of azo group and 260nm is due to absorption of formed amino group. This catalytic reaction can be easily followed spectrophotometrically, since the λ max of methyl orange is well separated from the surface Plasmon absorption of Fe₂O₃ Nanoparticles.



Figure 3. FESEM Images of Fe₂O₃ Nanoparticles.

The reduction of methyl orange by NaBH₄ in the absence of Fe₂O₃ Nanoparticles catalyst is extremely slow. This is evident from the observation that the intensity of λ max at 464 nm remains almost unchanged for several hours when a blank experiment is carried out without Fe₂O₃ nanoparticles catalyst. Thus, this reaction is not kinetically favorable in the absence of the catalyst and could not be realized only with NaBH₄. But the degradation reaction started immediately upon the addition of Fe₂O₃ nanoparticles as catalyst. The kinetics of Fe₂O₃ Nanoparticles catalyzed degradation of methyl orange by NaBH₄ was studied spectrophotometrically by monitoring the change in intensity of the absorption peak at 464 nm. As soon as the catalyst was added, the absorbance at 464 nm decreased continuously with time. The reaction was completed in 10 min as was evident from almost zero absorption at 464 nm. Electron transfer plays the crucial role in the degradation of methyl orange hinders the electron transfer between them [15]. Thus, the reduction of methyl orange by NaBH₄ in the absence of the nanocatalyst is thermodynamically favorable and not kinetically. Fe₂O₃ Nanoparticles catalyst provides an alternative path of low activation energy for the reaction and hence reduces the kinetic barrier thereby making it thermodynamically as well as kinetically favorable [16].



Figure 4. Pane (a) shows Decrease in Methyl Orange absorbance at 465 nm over time using Fe_2O_3 nanoparticles as catalyst in the presence of NaBH₄ at 303 K temperature and panel (b) shows decrease in methyl orange absorbance at 465 nm over time by uncatalyzed reaction with NaBH₄.

Kinetics and catalytic activity of Fe_2O_3 nanoparticles: The kinetics study was performed by using Langmuir-Hinshelwood mechanism [17]. The interaction of NaBH4 on the surface of Fe_2O_3 nanoparticles took place and which ultimately led to the liberation of hydrogen. In general, the rate law for degradation of methyl orange by NaBH₄ is given by Equation (1),

www.joac.info

$$-d [MO]/dt = k [MO]^{a} [BH_{4}]^{b} -(1)$$

In the Eq. (1) k is the pseudo-first order rate constant, calculated from Langmuir-Hinshelwood equation given by equation (2).

$$\ln(A_o/A_t) = kt - (2)$$

n the Eq. (2), A_0 and A_t are the initial and final absorptions monitored for fixed wavelength at time t, k is the pseudo-first order rate constant for Fe₂O₃ nanoparticles. Hence, for the constant catalyst concentration, a plot of ln(A0/At) with respect to time gives straight line having slope k showing in figure 5. The rate constant of degradation on methyl orange by NaBH₄ in presence of Fe₂O₃ Nanoparticles at 303 K was estimated to be 0.243 min⁻¹.



Figure 5. The Pseudo-first order reaction rate constant determined using Langmuir-Hinshelwood model by plotting $ln(A_0/At)$ vs Time.

Table 1. shows rate constants for degradation of methyl orange.

Degradation of methyl orange	Rate Constant (k) min ⁻¹
By NaBH ₄	0.038
By NaBH ₄ + Fe ₂ O ₃ Nanoparticles	0.243

APPLICATION

 Fe_2O_3Nps can be used as catalyst for removal of rigorous environmental pollutant dyes such as methyl orange. In the present investigation, it was observed that the Fe_2O_3Nps performed better for catalytic activity for degradation of methyl orange. The use of Fe_2O_3Nps will discover its use in various fields in years to come.

CONCLUSIONS

The catalytic activities of Fe_2O_3Nps have been determined by measuring the rate constant (k) using UV–Visible spectroscopy for the degradation of methyl orange in presence of NaBH₄. On the addition of Fe_2O_3NPs into methyl orange dye, rate of degradation is boost significantly indicating the improved catalytic behavior of Fe_2O_3NPs but in absence of Fe_2O_3NPs , the rate of degradation of methyl orange dye is very negligible.

ACKNOWLEDGEMENTS

Authors are thankful to Vice-Chancellor Research Motivation Scheme (VCRMS) North Maharashtra University, Jalgaon. Authors are also thankful to Department of chemistry, Moolji Jaitha College, Jalgaon for providing the laboratory facilities.

REFERENCES

- [1]. H.Yan, X.Tao, Z.Yang, K.Li, H.Yang, A.Li, R.Cheng, Effects of the oxidation degree of graphene oxide on the adsorption of methylene blue, *Journal of hazardous materials*, **2014**, 268,191-8.
- [2]. D. Ozdes, A. Gundogdu, C. Duran, H. Senturk, Evaluation of Adsorption characteristics of malachite green on to almond shell (*Prunus Dulcis*), *Separation Science and Technology*, 2010, 45(14), 2076-85.
 a) H. P. Narkhede, Solid Supported Synthesis of Bio-Active N-Alkyl Carbazole compounds using Microwaves, *J. Applicable Chem.*, 2014, 3(2), 678-682.

b) H. P.Narkhede and P. P.Mahulikar Microwave Induced Synthesis of Biologically active synthesis of N-acyloxy Phthalimides compounds, *J. Applicable Chem*, **2015**, 4(1), 337-341.

c) J. D Bhirud and H.P. Narkhede, Postassium dihydrogen phosphate: An Inexpensive catalyst for the synthesis of 2, 4, 5-Trisubstituted imidazoles under solvent free condition, *J. Applicable Chem.* **2016**, 5(5), 1075-19.

- [3]. D. K. Bozanic, L. V. Trandafilovic, A. S. Luyt, V. Djokovic, 'Green'synthesis and optical properties of silver-chitosan complexes and nanocomposites, *Reactive and functional polymers*, **2010**, 1,70(11), 869-73.
- [4]. K. R. Gopidas, J. K. Whitesell, M. A. Fox, Synthesis, characterization, and catalytic applications of a palladium-nanoparticle-cored dendrimer, *Nano Letters*, **2003**,3(12),1757-60.
- [5]. K. I. Fujita, S. Umeki, M. Yamazaki, T. Ainoya, T. Tsuchimoto, H. Yasuda, Magnetically recoverable osmium catalysts for dihydroxylation of olefins, *Tetrahedron letters*, **2011**, 52(24),3137-40.
- [6]. S. Luo, X. Zheng, J. P. Cheng, Asymmetric bifunctional primary aminocatalysis on magnetic nanoparticles, *Chemical communications*, **2008**, (44), 5719-21.
- [7]. A. Bhankhar, M. Giri, K. Yadav, N. Jaggi, Study on degradation of methyl orange an Azo dye by Fe₂O₃ Nanoparticles using UV-Visible Spectroscopy, *Indian J. Phys*, **2014**, 88 (11), 1191-1196.
- [8]. H. R. Pouretedal, H. Eskandarih, M. H. Keshavarz, A. Semnani, Photodegration of organic dyes using Nagoparticles of Cadmium sulfide doped with Manganese, Nickel and Coppers as Nanophotocatalyst, *Acta Chemica Slovenica*, 2009, 56 (2).
 a) D.Paliwal, H. Sankar Sharma, R. Ameta, B.Kataria, Photocaalytic Degradation of Malachite green over CuO/AL2O3 Composite, *J. Applicable Chem*, 2018, 7(1), 130-137.
- [9]. K. Bubacz, J. Choina, D. Dolat, A.W. Morawski, Methylene Blue and Phenol Photocatalytic Degradation on Nanoparticles of Anatase TiO₂, *Polish Journal of Environmental Studies*, 2010, 19(4).
- [10]. R. Byberg, J. Cobb, Photocatalytic degradation of a series of direct azo dyes using immobilized TiO₂, Worcester Polytechnic Institute. **2012** Mar 3:1-66.
- [11]. F. J. Green, The Sigma-Aldrich handbook of stains, dyes and indicators, Aldrich Chemical Co, 1990.
- [12]. C. B. Wang, W. X. Zhang, Synthesizing nanoscale iron particles for rapid and complete dechlorination of TCE and PCBs, *Environ. Sci. Technol*, **1997**, 31(7), 2154-2156.
- [13]. T. Phenrat, N.Saleh, K Sirk, R.D.Tilton, G.V.Lowry, Aggregation and sedimentation of aqueous nanoscale zerovalent iron dispersions, *Environmental Science & Technology*, 2007, 41(1),284-90.
- [14]. Y. Zheng, A.Wang, Ag nanoparticle-entrapped hydrogel as promising material for catalytic reduction of organic dyes, *Journal of Materials Chemistry*, **2012**, 22(32), 16552-9.
- [15]. N. R. Jana, T. K. Sau, T. Pal, Growing small silver particle as redox catalyst, *The Journal of Physical Chemistry B*, **1999**,103(1),115-21.
- [16]. K. Mallick, M. Witcomb, M. Scurrell, Silver nanoparticle catalysed redox reaction: an electron relay effect, *Materials chemistry and physics*, 2006, 97(2-3), 283-7.
- [17]. N. Agmon, R. D. Levine, Energy, entropy and the reaction coordinate: thermodynamic-like relations in chemical kinetics, *Chemical Physics Letters*, **1977**, 52(2), 197-201.